Version number 4

Printing date 07.09.2022

Revision: 07.09.2022



Version number 4

Revision: 07.09.2022

Trade name: Dodecylsulfate-Na-salt

Printing date 07.09.2022

	(Contd. of page 1)
H318	Causes serious eye damage.
H335	May cause respiratory irritation.
H412	Harmful to aquatic life with long lasting effects.
	ary statements
P273	Avoid release to the environment.
P280	Wear protective gloves/protective clothing/eye protection/face protection/hearing protection.
P301+P312	2 IF SWALLOWED: Call a POISON CENTER/doctor if you feel unwell.
P302+P352	2 IF ON SKIN: Wash with plenty of soap and water.
P304+P340	
P305+P35	1+P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if
	present and easy to do. Continue rinsing.
· Labelling a	of packages where the contents do not exceed 125 ml
	tograms GHS05, GHS07
· Signal wor	
· Hazard sta	
H318 Caus	es serious eye damage.
· Precaution	ary statements
P280	Wear protective gloves/protective clothing/eye protection/face protection/hearing
	protection.
P302+P352	<i>IF ON SKIN: Wash with plenty of soap and water.</i>
P305+P35	1+P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if
	present and easy to do. Continue rinsing.
· 2.3 Other h	
· Results of	PBT and vPvB assessment:
•	- assessment not available.
	B - assessment not available.
SECTIO N	3: Composition/information on ingredients
2 1 Substa	
· 3.1 Substar	
• CAS No. D	
	odium dodecyl sulphate
	ion number(s):
• EC number	
• Description	
	formula: C ₁₂ H ₂₅ O ₄ S Na
• MW: 288.3	
· Regulation	(EC) No 648/2004 on detergents / Labelling for contents
anionic sur	factants ≥30%
SECTION	4: First aid measures

• 4.1 Description of first aid measures

- After inhalation: Supply fresh air; consult doctor in case of complaints.
- After skin contact:
- Immediately wash with water and soap and rinse thoroughly. Consult doctor if you feel unwell.
- · After eye contact:

Rinse opened eye for several minutes under running water. Remove present contact lenses, if easy to do, and continue rinsing. Consult ophthalmologist immediately.

• After swallowing:

Wash out mouth instantly. Drink copious amounts of water and provide fresh air. Call for doctor immediately.

• 4.2 Most important symptoms and effects, both acute and delayed Coughing

(Contd. on page 3)

GB

Printing date 07.09.2022

Version number 4

Revision: 07.09.2022

Trade name: Dodecylsulfate-Na-salt

Breathing difficulty

• 4.3 Indication of any immediate medical attention and special treatment needed

No further relevant information available.

SECTION 5: Firefighting measures

· 5.1 Extinguishing media

- Suitable extinguishing agents:
- CO₂, extinguishing powder or water spray. Fight larger fires with water spray or alcohol resistant foam.
- \cdot 5.2 Special hazards arising from the substance or mixture:
- In case of fire, the following can be formed, but not limited to:
- Carbon monoxide and carbon dioxide
- Sulphur oxides (SOx)
- 5.3 Advice for firefighters
 Protective equipment: Wear self-contained respiratory protective device.
- · Additional information

Collect contaminated fire fighting water separately. It must not enter the sewage system.

SECTION 6: Accidental release measures

- 6.1 Personal precautions, protective equipment and emergency procedures Wear protective clothing. Ensure adequate ventilation Avoid formation of dust. Avoid contact with the eyes and skin.
 6.2 Environmental precautions: Do not allow to enter sewers/ surface or ground water.
- 6.3 Methods and material for containment and cleaning up Dispose contaminated material as waste according to item 13. Pick up mechanically.
- 6.4 Reference to other sections
 See Section 7 for information on safe handling
 See Section 8 for information on personal protection equipment.
 See Section 13 for disposal information.

SECTION 7: Handling and storage

- 7.1 Precautions for safe handling: No special precautions are necessary if used correctly.
- · Information about protection against explosions and fires: Protect against electrostatic charges.
- · 7.2 Conditions for safe storage, including any incompatibilities
- · Storage
- *Requirements to be met by storerooms and receptacles:* Store only in unopened original receptacles. Store in a cool location.
- · Information about storage in one common storage facility: Not required.
- Further information about storage conditions: Store under lock and key and with access restricted to technical experts or their assistants only. Keep receptacle tightly sealed and store in dry conditions.
- 7.3 Specific end use(s): No further relevant information available.

SECTION 8: Exposure controls/personal protection

- · 8.1 Control parameters
- Components with limit values that require monitoring at the workplace: Not required.
- Additional information: The lists that were valid during the creation were used as basis.

(Contd. on page 4)

(Contd. of page 2)

Printing date 07.09.2022

*

Version number 4

Revision: 07.09.2022

Trade name: Dodecylsulfate-Na-salt

Short term filter device: Filter P2. Hand protection: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Protective gloves. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and th degradation Material of gloves: The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. Penetration time of glove material: The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials and suitable: Section 9: Physical and chemical properties General Information: Physical state: Solid. Colour: Odour threshold: Not determined. Metting point or initial boiling point and boiling range: Flammability: Based on available flammabile solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable. Lower: no information available Flash point: Secondo State: Solid. Colour: Not dependent and the solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable. Lower: no information available Flash point: Solid Colouris Solid Colouris Solid Colouris Solid State: Solid		(Contd. of page
Individual protection measures, such as personal protective equipment: General protective and hygienic measures: Keep away from foodstuffs, beverages and feed. Store protective clothing separately. Immediately remove all solied and comaminated clothing Avoid contact with the eyes and skin. Wash hands before breaks and at the end of work. Breathing equipment: Short term filter device: Filter P2. Hand protection: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Protective gloves. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation. Protective gloves. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation. the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves: The selection of the suitable gloves does not only depend on the material, but also on further marks - quality and varies from manufacturer to manufacturer. Penetration time of glove material: The exact break trough time has to be found out by the manufacturer of the protective gloves and has to 1 observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials an suitable: Nitrile rubber, NBR Chloroprene rubber, CR Fyelface protection: Tightly sealed goggles. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information: Physical state: Colour: Muite Odour threshold: Metting point or initial boiling point and boiling range: Flammability: Flammability: Flammability: Flammability: Dever and upper explosion limit: Lower: Dever and upper explosion lim		
General protective and hygienic measures: Keep away from foodstuffs, beverages and feed. Store protective clothing separately. Immediately remove all solied and commaniated clothing Avoid contact with the eyes and skin. Wash hands before breaks and at the end of work. Breathing equipment: Short term filter device: Filter P2. Hand protection: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Protective gloves. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation. Protective gloves. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation. the chemical mixture. Selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacture to manufacturer. Penetration time of glove material: The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacture to manufacturer. Penetration time of glove material: The exact break trough time has to be found out by the manufacturer of the protective gloves and has to b observed. Sectorion: Thyle sealed goggles. Body protection: Protective work clothing. Sectorions on basic physical and chemical properties General Information: Physical state: Colour: Muite Odour threshold: Not determined. Odour threshold: Not determined. Dol-207 °C Boiling point or initial boiling point and boiling range: Flammability: Flammability: Not determined. Dol-207 °C Boiling point or initial boiling point and boiling range: Flammability: Protention constant of a maximum of 15 minutes and available Based on available data, the classification criteria of filammabile solids are not met. burning time (sample length 200 mm, UN test N. I preliminary test): > 120 seconds Highly flammable. Lower: no information available Plash point: Secondstion temperature: No inform		
Keep away from foodstuffs, beverages and feed. Store protective clothing separately. Immediately remove all solied and commaninated clothing Avoid contact with the eyes and skin. Wash hands before breaks and at the end of work. Breathing equipment: Short term filter device: Filter P2. Hand protection: The glow material has to be impermeable and resistant to the product/ the substance/ the preparation. Protective gloves. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation. Protective gloves in recommendation to the glove material can be given for the product/ the preparation the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and tid degradation Material of gloves: The sale tests no recommendation to the glove material can be given for the product/ the preparation. Material of gloves: The sale tests of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer. Penetration time of glove material: The exact break trough time has to be found out by the manufacturer of the protective gloves and has to le observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials an suitable: Nitrile rubber, NBR Chloroprene rubber, CR Eyeface protection: Tightly sealed goggles. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information: Physical state: Colour:		
Store protective clothing separately. Immediately remove all soiled and contaminated clothing Avoid contact with the eyes and skin. Wash hands before breaks and at the end of work. Breathing equipment: Short term filter device: Filter P2. Hand protection: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Protective gloves. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation. Protective gloves. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and ti degradation Material of gloves: The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. Penetration time of glove material The sect break trough time has to be found out by the manufacturer of the protective gloves and has to 1 observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials at suitable: Ntrile rubber, NBR Chloroprene rubber, CR Eyeface protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information: Physical state: Odour: Odourtess Odour threshold: Not determined. Metting point/freezing point: Odourtess Odour threshold: Not determined. Lower: Not gloves are not met. During time (sample length 200 mm, UN test N. I preliminary test): > 120 seconds Highly flammable. Lower: Not gloves Not glo		
Immediately remove all soiled and contaminated clothing Avoid contact with the eyes and skin. Wash hands before breaks and at the end of work. Breathing equipment: Short term filter device: Filter P2. Hand protection: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Protective gloves. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and th degradation Material of gloves: The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. Penetration time of glove material: The exact break trough time has to be found out by the manufacturer of the protective gloves and has to 1 observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials an suitable: Nurrile rubber, NBR Chloroprene rubber, CR Eveface protection: Tightly sealed goggles. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information: Physical state: Solid. Colour: White Odour: Odourthreshold: Not determined. Metting point(freeing point: 204-207 °C Boiling point or initial boiling point and boiling runge: Not determined. During time (sample length 200 mm, UN test N. I preliminary test):> 120 seconds Highly flammables. Lower: no information available Flammability: Solid Colour: Not determined. Colour: Not determined		d feed.
Avoid comlact with the eyes and skin. Wash hands before breaks and a the end of work. Breathing equipment: Short term filter device: Filter P2. Hand protection: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Protective gloves. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and th degradation Material of gloves: The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. Penetration time of glove material: The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials an suitable: Nirtile rubber, NBR Chioroprene rubber, CR Eye/face protection: Fighty sealed goggles. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information Mething point or initial boiling point and boiling range: Flust go int or initial boiling point and boiling range: Flust go int or initial boiling point and boiling range: Flust go int or initial boiling point and boiling range: Flummability: Lower and upper explosion limit: Lower: no information available Flush point: Lower: no information available		
Wash hands before breaks and at the end of work. Breathing equipment: Short term filter device: Filter P2. Hand protection: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Protective gloves. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and th degradation Material of gloves: The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. Penetration time of glove material: The exact break trough time has to be found out by the manufacturer of the protective gloves and has to to observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials at suitable: Selection: Triphily sealed goggles. Body protection: Protective work clothing. Selection: Physical and chemical properties General Information on basic physical and chemical properties Odour: Odourie: Odourie: Odourie: Odourie: Colour: Colour		minated clothing
Breathing equipment: Short term filter device: Filter P2. Hand protection: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Protective gloves. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves: The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. Penetration time of glove material: The selection of the suitable gloves does not only depend on the material, but also on further marks of austing tests to be found out by the manufacturer of the protective gloves and has to bobserved. For the permanent contact of a maximum of 15 minutes gloves made of the following materials at suitable: Nitrile rubber, NBR Chloroprene rubber, CR Speiface protection: Tightly sealed goggles. Body protection: Tightly sealed goggles. Portection: Tightly sealed goggles. Polysical state: Solid. Colour: White Odouriers Odourlers Odour threshold: Not determined.		
Short term filter device: Filter P2. Hand protection: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Protective gloves. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation the chemical misture. Selection of the glove material on consideration of the penetration times, rates of diffusion and th degradation Material of gloves: The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. Penetration time of glove material: The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Nitrile rubber, NBR Chloroprene nubber, CR Eye/face protection: Tightly sealed goggles. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information: Physical state: Odour: Odour threshold: Not determined. Multing point or initial boiling point and boiling range: Flammability: Based on avaitable data, the classification criteria of filammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable. Lower: No information available Flash point: Decomposition temperature: No information available Flash point: Decomposition temperature: No information available		l of work.
Filter P2. Hand protection: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Protective gloves. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation the chemical misture. Selection of the glove material on consideration of the penetration times, rates of diffusion and th degradation Material of gloves: The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. Penetration time of glove material: The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials an suitable: Nitrile rubber, NBR Chloroprene rubber, CR Eyeface protection: Tightly sealed goggles. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information Colour: Odour: Odourles Odour threshold: Not determined. Not de		
Hand protection: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Protective gloves. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves: The selection of the suitable gloves does not only depend on the material, but also on further marks or quality and varies from manufacturer to manufacturer. Penetration time of glove material: The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials an suitable: Nitrile rubber, NBR Chloroprene rubber, CR Eyefface protection: Tightly sealed goggles. Boy protection: Protective work clothing. 9.1 Information on basic physical and chemical properties General Information: Physical state: Solid. Colour: Odourless Odour threshold: Not determined. Postical state: Solid. Colour: Based on available Flammability: Based on available data, the classification c		
The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Protective gloves. Protective gloves. Selection of the glove material on consideration of the penetration times, rates of diffusion and th degradation Material of gloves: The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. Penetration time of glove material: The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. Penetration time of glove material: The exact break trough time has to be found out by the manufacturer of the protective gloves and has to b observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials an suitable: Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed goggles. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information Physical state: Colour: Odour: Odour threshold: Not determined. Metting point/freezing point: 204-207 °C Boiling point or initial boiling point and boiling range: Flammability: Lower: Not determined. Highly flammable. Lower: Not determined. Lower: Not of explosion limit: Lower: Not of explosion limit: Not of explosion limit: Not of explosion limit: Not of explosion limit: Not of explosion and boiling Flash point: Not of explosion and boiling Chloroprection: Not of explosion limit: Not of explosion limit: Not of explosion limit: Not of explosion and boiling Physical state: Not of the glove for the state boiling Physical point: Not determined. Physical point: Not determined. Physical point: Not determined. Physical point or initial boiling point and boiling Physical state: Not determined. Physical point: Not determined. Physical point: Not determined. Physical point: Not determined. Physical point poin		
Protective gloves. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves: The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. Penetration time of glove material: The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials an suitable: Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed goggles. Body protection: Protective work clothing. Section: Vitie Odour: Odourless Odour: Odourless Odour: Odourless Odour threshold: Not determined. Metring point/freezing point: 204-207 °C Boiling point or initial boiling point and boiling range: no information available Flammability: Based on available data, the classification criteria of flammables solids are not met. burrning time (sample length 200 mm, UN test N. 1 preliminary		le and resistant to the product the substance the propagation
Due to missing tests no recommendation to the glove material can be given for the product/ the preparation the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves: The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. Penetration time of glove material: The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials an suitable: Nitrile rubber, NBR Chioroprene rubber, CR Eyefface protection: Tightly sealed goggles. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information: Physical state: Godour: Godour: Godour: Godour threshold: Godour threshold: Flammability: Fl		e and resistant to the product/ the substance/ the preparation.
the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves: The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. Penetration time of glove material: The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials an suitable: Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed goggles. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information: Physical state: Solid. Colour: White Odour: Odouries Odouries Not determined. Metting point or initial boiling point and boiling range: no information available Flammability: Lower and upper explosion limit: Lower: Not material and upper explosion limit: Lower: Not material and upper explosion limit: Lower: Not material and available SISS CC Colour: Not determined available Not determined and boiling Flash point: SISS CC Not and the classification criteria of flammable solids are not met. Deven and upper explosion limit: Lower: Not per the solid in temperature: Not per temperature: Not per temperature: Not per temperature: Not determined and the solid are not met. Not determined. Not determined. Support of the solid are not met. Supreminary test): > 120 seconds Highly flammable. Not determined available Support of the solid are not met. Not performation available Support of the solid are not met. Not performation available Support of the solid are not met. Supreminary test): > 120 seconds Highly flammable. Not performat		to the alove material can be given for the product the propagation
Selection of the glove material on consideration of the penetration times, rates of diffusion and th degradation Material of gloves: The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. Penetration time of glove material: The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials an suitable: Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed goggles. Body protection: Trightly sealed goggles. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information Odour: Odour: Odour threshold: Not determined. Metting point/freezing point: Solid. Flammability: Boiling point or initial boiling point and boiling range: no information available flammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable. Lower: no information available Flash point: Decomposition temperature: no information available Flash point: Decomposition temperature: no information available	0	to the glove material can be given for the product, the preparation
degradation Material of gloves: Material of gloves: Material of gloves: The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. Penetration time of glove material: The exact break trough time has to be found out by the manufacturer of the protective gloves and has to b observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials an suitable: Nitrile rubber, NBR Chloroprene rubber, CR Eyeiface protection: Tightly sealed goggles. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information: Physical state: Solid. Not determined. 204-207 °C Boiling point or initial boiling point and boiling gange: no information available Flammability: Lower and upper explosion limit: Lower: Not information available Not information available Not information available Not information available Not preliminary test;: > 120 seconds Highly flammable. Lower and upper explosion limit: Lower: Not information available Not information available Not information available Not preliminary test;: > 120 seconds Highly flammable. Not preliminary test;: > 120 seconds Highly flammable. Not information available Not information available Not preliminary test;: > 120 seconds Highly flammable. Not information available Not preliminary test;: > 120 seconds Highly flammable. Not preliminary test;: > 120 seconds Highly		nsideration of the nenetration times rates of diffusion and th
Material of gloves: The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. Penetration time of glove material: The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials an suitable: Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed goggles. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information: Physical state: Solid. Colour: White Odour threshold: Not determined. Melting point/freezing point: 204-207 °C Boiling point or initial boiling point and boiling range: no information available Flammability: Based on available data, the classification criteria of flammable. Lower and upper explosion limit: Lower: no information available Lower: no information available 11 Preperiminary test]: > 120 seconds 11 Preperiminary test]: > 120 seconds 11 Prepriminary test]:		nsueration of the penetration times, rates of affusion and th
The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. Penetration time of glove material: The exact break trough time has to be found out by the manufacturer of the protective gloves and has to b observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials an suitable: Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed goggles. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties Observed. Odour: Odourless Odour threshold: Not determined. Multing point/freezing point: 204-207 °C Boiling point or initial boiling point and boiling range: no information available Flammability: Based on available data, the classification criteria of filammable. Lower: no information available Flash point: >150 °C Dec		
quality and varies from manufacturer to manufacturer. Penetration time of glove material: The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be fouserved. For the permanent contact of a maximum of 15 minutes gloves made of the following materials an suitable: Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed goggles. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information: Physical state: Solid. Colour: White Odour: Odourless Odour threshold: Not determined. Metting point/freezing point: 204-207 °C Boiling point or initial boiling point and boiling ravialable data, the classification criteria of filammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable. Lower: no information available Lower: no information available Highly flammable. Lower: no information available Flash point: Decomposition temperature:		es not only depend on the material but also on further marks o
Penetration time of glove material: The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials and suitable: Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed goggles. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information: Physical state: Solid. Colour: White Odour threshold: Not determined. Oding point or initial boiling point and boiling no information available Flammability: Based on available data, the classification criteria of filammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable. Lower: no information available Lower: no information available Plash point: >150 °C Decomposition temperature: no information available		
The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials an suitable: Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed goggles. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information: Physical state: Solid. Colour: Odourless Odour threshold: Not determined. Oding point freezing point: 204-207 °C Boiling point or initial boiling point and boiling range: no information available Flammability: Based on available data, the classification criteria of flammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable. Lower and upper explosion limit: no information available Lower: no information available Plash point: >150 °C Decomposition temperature: no information available		nunnig uch nin en
observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials at suitable: Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed goggles. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information: Physical state: Solid. Colour: Odour threshold: Not determined. Odourless Odour threshold: Not determined. Melting point/freezing point: 204-207 °C Boiling point or initial boiling point and boiling range: Flammability: Not determined. Based on available data, the classification criteria of flammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable. Lower: Not information available Physical boint: Lower: Not information available Flash point: Solid.		ound out by the manufacturer of the protective gloves and has to h
For the permanent contact of a maximum of 15 minutes gloves made of the following materials and suitable: Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed goggles. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information: Physical state: Solid. Colour: Odourless Odour threshold: Not determined. Melting point/freezing point: 200 °C Boiling point or initial boiling point and boiling range: no information available Flammability: Based on available data, the classification criteria of filammable solids are not met. burget import explosion limit: Lower and upper explosion limit: Lower: no information available Upper: no information available Flash point: >150 °C Decomposition temperature: no information available		
suitable: Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed goggles. Body protection: Protective work clothing. 9.1 Information on basic physical and chemical properties General Information: Physical state: Colour: Odour: Odour: Odour: Odour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range: Flammability: Flammability: Lower and upper explosion limit: Lower: Not determined available Highly flammable. Lower: Decomposition temperature: Not determined available Not determined. Not determined. Solid. Colour: Odourless Solid. Colour: Solid. Colour: Solid. Colour: Solid. Colour: Solid. Colour: Solid. Colour: Solid. Colour: Solid. Colour: Solid. Solid		num of 15 minutes gloves made of the following materials ar
Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed goggles. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information: Physical state: Solid. Colour: Not determined. Odour threshold: Not determined. Melting point freezing point: Planmability: Flammability: Lower: Lower: Not information available Tabue the classification criteria of flammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable. Lower: Not information available Plash point: Solid: Lower: Not determined available Plash point: Solid: Solid: Not determined available Not determined. Solid: Not determined. Solid: Not determined. Solid: Not determined. Solid: Not determined. Solid: Not determined. Solid: Not determined. Solid: S		
Chloroprene rubber, CR Eye/face protection: Tightly sealed goggles. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information: Physical state: Solid. Colour: White Odouris: Odourless Odour threshold: Not determined. Oding point/freezing point: 204-207 °C Boiling point or initial boiling point and boiling range: no information available Flammability: Based on available data, the classification criteria of fflammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable. Lower and upper explosion limit: no information available Lower: no information available Flash point: >150 °C Decomposition temperature: no information available	SHUMPLE.	
Eye/face protection: Tightly sealed goggles. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information: Physical state: Solid. Colour: White Odouri: Odourless Odour threshold: Not determined. Melting point/freezing point: 204-207 °C Boiling point or initial boiling point and boiling no information available Flammability: Based on available data, the classification criteria of fflammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable. Highly flammable. Lower: no information available Upper: no information available Flash point: >150 °C Decomposition temperature: no information available		
Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information: Physical state: Solid. Colour: White Odouri: Odourless Odour threshold: Not determined. Melting point/freezing point: 204-207 °C Boiling point or initial boiling point and boiling range: no information available Flammability: Based on available data, the classification criteria of fflammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable. Highly flammable. Lower and upper explosion limit: no information available Lower: no information available Flash point: >150 °C Decomposition temperature: no information available	Nitrile rubber, NBR	
SECTION 9: Physical and chemical properties Section of the state of the	Nitrile rubber, NBR Chloroprene rubber, CR	les.
9.1 Information on basic physical and chemical properties General Information: Physical state: Solid. Colour: White Odour: Odourless Odour threshold: Not determined. Melting point/freezing point: 204-207 °C Boiling point or initial boiling point and boiling no information available range: no information available data, the classification criteria of fflammabile solids are not met. Flammability: Based on available data, the classification criteria of fflammabile solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable. Highly flammable. Lower: no information available Upper: no information available Flash point: >150 °C Decomposition temperature: no information available	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg	
9.1 Information on basic physical and chemical properties General Information: Physical state: Solid. Colour: White Odour: Odourless Odour threshold: Not determined. Melting point/freezing point: 204-207 °C Boiling point or initial boiling point and boiling no information available range: no information available data, the classification criteria of fflammabile solids are not met. Flammability: Based on available data, the classification criteria of fflammabile solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable. Highly flammable. Lower: no information available Upper: no information available Flash point: >150 °C Decomposition temperature: no information available	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg	
General Information:Physical state:Solid.Colour:WhiteOdour:OdourlessOdour threshold:Not determined.Melting point/freezing point:204-207 °CBoiling point or initial boiling point and boiling range:no information availableFlammability:Based on available data, the classification criteria o fflammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable.Lower and upper explosion limit:no information availableUpper:no information availableFlash point:>150 °CDecomposition temperature:no information available	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin	·g.
Physical state:Solid.Colour:WhiteOdour:OdourlessOdour threshold:Not determined.Melting point/freezing point:204-207 °CBoiling point or initial boiling point and boiling range:no information availableFlammability:Based on available data, the classification criteria o fflammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable.Lower:no information availableUpper:no information availableFlash point:>150 °C no information available	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin SECTION 9: Physical and chemical	g. properties
Colour:WhiteOdour:OdourlessOdour threshold:Not determined.Melting point/freezing point:204-207 °CBoiling point or initial boiling point and boiling range:no information availableFlammability:Based on available data, the classification criteria o fflammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable.Lower:no information availableUpper:no information availableFlash point:>150 °C no information available	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin SECTION 9: Physical and chemical 9.1 Information on basic physical and cl	g. properties
Odour:OdourlessOdour threshold:Not determined.Odour threshold:204-207 °CBoiling point or initial boiling point and boiling range:no information availableFlammability:Based on available data, the classification criteria of fflammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable.Lower and upper explosion limit:no information availableUpper:no information availableFlash point:>150 °C no information available	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin SECTION 9: Physical and chemical 9.1 Information on basic physical and cl General Information:	g. properties hemical properties
Odour threshold:Not determined.Melting point/freezing point:204-207 °CBoiling point or initial boiling point and boiling range:no information availableFlammability:Based on available data, the classification criteria of fflammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable.Lower:no information available no information availableUpper:no information available > 150 °C no information available	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin SECTION 9: Physical and chemical 9.1 Information on basic physical and chemical General Information: Physical state:	g. properties hemical properties Solid.
Melting point/freezing point:204-207 °CBoiling point or initial boiling point and boiling range:no information availableFlammability:Based on available data, the classification criteria of fflammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable.Lower and upper explosion limit: Upper:no information available no information availableUpper:no information available >>150 °C no information available	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin SECTION 9: Physical and chemical 9.1 Information on basic physical and chemical General Information: Physical state: Colour:	g. properties hemical properties Solid. White
Boiling point or initial boiling point and boiling range:no information availableFlammability:Based on available data, the classification criteria of fflammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable.Lower and upper explosion limit: Upper:no information available no information availableUpper: Flash point:no information available > >150 °C no information available	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin SECTION 9: Physical and chemical 9.1 Information on basic physical and cl General Information: Physical state: Colour: Odour:	properties hemical properties Solid. White Odourless
range:no information availableFlammability:Based on available data, the classification criteria of fflammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable.Lower and upper explosion limit:no information availableLower:no information availableUpper:no information availableFlash point:>150 °C no information available	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin SECTION 9: Physical and chemical 9.1 Information on basic physical and cl General Information: Physical state: Colour: Odour: Odour threshold:	properties hemical properties Solid. White Odourless Not determined.
Flammability:Based on available data, the classification criteria of fflammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable.Lower and upper explosion limit: Lower:no information available no information availableUpper: Flash point:>150 °C no information available	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin SECTION 9: Physical and chemical 9.1 Information on basic physical and ch General Information: Physical state: Colour: Odour: Odour threshold: Melting point/freezing point:	properties hemical properties Solid. White Odourless Not determined. 204-207 °C
fflammable solids are not met.burning time (sample length 200 mm, UN test N. 1preliminary test): > 120 secondsHighly flammable.Lower:no information availableUpper:no information availableFlash point:>150 °CDecomposition temperature:no information available	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin SECTION 9: Physical and chemical 9.1 Information on basic physical and cl General Information: Physical state: Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and	properties hemical properties Solid. White Odourless Not determined. 204-207 °C
burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable.Lower and upper explosion limit:Lower:no information available no information availableUpper:no information available > >150 °C no information available	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin SECTION 9: Physical and chemical 9.1 Information on basic physical and cl General Information: Physical state: Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and range:	properties hemical properties Solid. White Odourless Not determined. 204-207 °C I boiling no information available
preliminary test): > 120 seconds Highly flammable.Lower and upper explosion limit:Lower:no information availableUpper:no information availableFlash point:>150 °CDecomposition temperature:no information available	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin SECTION 9: Physical and chemical 9.1 Information on basic physical and cl General Information: Physical state: Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and range:	properties hemical properties Solid. White Odourless Not determined. 204-207 °C I boiling no information available Based on available
Highly flammable.Lower and upper explosion limit:Lower:no information availableUpper:no information availableFlash point:>150 °CDecomposition temperature:no information available	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin SECTION 9: Physical and chemical 9.1 Information on basic physical and cl General Information: Physical state: Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and range:	properties hemical properties Solid. White Odourless Not determined. 204-207 °C I boiling no information available Based on available data, the classification criteria of flammable solids are not met.
Lower and upper explosion limit:Lower:no information availableUpper:no information availableFlash point:>150 °CDecomposition temperature:no information available	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin SECTION 9: Physical and chemical 9.1 Information on basic physical and cl General Information: Physical state: Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and range:	properties hemical properties Solid. White Odourless Not determined. 204-207 °C I boiling no information available Based on available data, the classification criteria of fflammable solids are not met. burning time (sample length 200 mm, UN test N. 1
Lower:no information availableUpper:no information availableFlash point:>150 °CDecomposition temperature:no information available	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin SECTION 9: Physical and chemical 9.1 Information on basic physical and cl General Information: Physical state: Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and range:	properties hemical properties Solid. White Odourless Not determined. 204-207 °C I boiling no information available Based on available data, the classification criteria of fflammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds
Upper:no information availableFlash point:>150 °CDecomposition temperature:no information available	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin SECTION 9: Physical and chemical 9.1 Information on basic physical and ch General Information: Physical state: Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and range: Flammability:	properties hemical properties Solid. White Odourless Not determined. 204-207 °C I boiling no information available Based on available data, the classification criteria of fflammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds
Flash point:>150 °CDecomposition temperature:no information available	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin SECTION 9: Physical and chemical 9.1 Information on basic physical and ch General Information: Physical state: Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and range: Flammability:	properties hemical properties Solid. White Odourless Not determined. 204-207 °C I boiling no information available Based on available data, the classification criteria of fflammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable.
Decomposition temperature: no information available	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin SECTION 9: Physical and chemical 9.1 Information on basic physical and cl General Information: Physical state: Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and range: Flammability: Lower and upper explosion limit: Lower:	properties hemical properties Solid. White Odourless Not determined. 204-207 °C I boiling no information available Based on available data, the classification criteria of fflammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable. no information available
	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin SECTION 9: Physical and chemical 9.1 Information on basic physical and cl General Information: Physical state: Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and range: Flammability: Lower and upper explosion limit: Lower: Upper:	g. properties hemical properties Solid. White Odourless Not determined. 204-207 °C I boiling no information available Based on available data, the classification criteria of fflammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable. no information available no information available
рн: 6-У	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin SECTION 9: Physical and chemical 9.1 Information on basic physical and cl General Information: Physical state: Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and range: Flammability: Lower and upper explosion limit: Lower: Upper: Flash point:	properties hemical properties Solid. White Odourless Not determined. 204-207 °C I boiling no information available Based on available data, the classification criteria of fflammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable. no information available no information available no information available >150 °C
	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin SECTION 9: Physical and chemical 9.1 Information on basic physical and cl General Information: Physical state: Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and range: Flammability: Lower and upper explosion limit: Lower: Upper: Flash point: Decomposition temperature:	properties hemical properties Solid. White Odourless Not determined. 204-207 °C I boiling no information available Based on available data, the classification criteria of fflammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable. no information available no information available no information available > 150 °C no information available
	Nitrile rubber, NBR Chloroprene rubber, CR Eye/face protection: Tightly sealed gogg Body protection: Protective work clothin SECTION 9: Physical and chemical 9.1 Information on basic physical and cl General Information: Physical state: Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and range: Flammability: Lower and upper explosion limit: Lower: Upper: Flash point: Decomposition temperature:	properties hemical properties Solid. White Odourless Not determined. 204-207 °C I boiling no information available Based on available data, the classification criteria of filammable solids are not met. burning time (sample length 200 mm, UN test N. 1 preliminary test): > 120 seconds Highly flammable. no information available no information available no information available >150 °C no information available

Printing date 07.09.2022

Version number 4

Revision: 07.09.2022

Trade name: Dodecylsulfate-Na-salt

	(Contd. of page 4
· Viscosity:	
· Kinematic viscosity:	no information available
· Dynamic viscosity:	no information available
· Solubility:	·
· Water:	Soluble
· Partition coefficient n-octanol/water (log value):	log Pow (22°C): 0,83
• Vapour pressure at 20 °C:	0.0018 hPa
· Density and/or relative density:	
· Density:	Not determined
· Relative density:	no information available
· Particle characteristics	No information available
· 9.2 Other information	There are no more data available.
· Appearance:	
· Form:	Flakes
· Important information on protection of health and	d
environment, and on safety:	
· Ignition temperature:	no information available
· Explosive properties:	Product is not explosive. However, formation of explosive dust-/air mixtures are possible.

SECTION 10: Stability and reactivity

· 10.1 Reactivity: No further relevant informations available

- · 10.2 Chemical stability:
- Thermal decomposition / conditions to be avoided: No decomposition if used according to specifications.
- 10.3 Possibility of hazardous reactions: As the product is supplied it is not capable of dust explosion; however enrichment with fine dust causes risk of dust explosion
- 10.4 Conditions to avoid:
- Avoid high temperatures, flames, sparks moisture
- · 10.5 Incompatible materials: Avoid contact with strong oxidizers.
- 10.6 Hazardous decomposition products: In case of fire: See Section 5
- **SECTION 11: Toxicological information**
- 11.1 Information on hazard classes as defined in Regulation (EC) No 1272/2008:
- · Acute toxicity: Harmful if swallowed or if inhaled.

· LD/LC50 values that are relevant for classification:

		9
Oral	LD50	1,288 mg/kg (rat)
Dermal	LD50	1,288 mg/kg (rat) >2,000 mg/kg (rabbit)
Inhalative	LC50	>3.9 /mg/l - 1h (rat)

· Skin corrosion/irritation: Causes skin irritation.

- · Serious eye damage/irritation: Causes serious eye damage.
- Respiratory or skin sensitisation: Based on available data, the classification criteria are not met.
- · Germ cell mutagenicity: Based on available data, the classification criteria are not met.
- · Carcinogenicity: Based on available data, the classification criteria are not met.
- · Reproductive toxicity: Based on available data, the classification criteria are not met.
- · STOT-single exposure: May cause respiratory irritation.
- STOT-repeated exposure: Based on available data, the classification criteria are not met.
- · Aspiration hazard: Based on available data, the classification criteria are not met.

(Contd. on page 6)

GB

Printing date 07.09.2022

Version number 4

Revision: 07.09.2022

(Contd. of page 5)

Trade name: Dodecylsulfate-Na-salt

- · 11.2 Information on other hazards:
- Endocrine disrupting properties: Substance is not listed.
- **SECTION 12: Ecological information**
- · 12.1 Toxicity:
- Aquatic toxicity: LC50/48h (Daphnia dubia): 5,55 mg/l NOEC (Daphnia dubia, 7 d): 0,684 mg/l Toxicity to fish: LC50/96h (pimephales promelas) 29 mg/l
- **12.2 Persistence and degradability:** Biodegradability: 95 % in 28 d the product is readily biodegradable. 90% (28 d)
- 12.3 Bioaccumulative potential: Bioconcentrationfactor: 3,9-5,3 (72h), Cyprinus carpio Distribution coefficient n-octanol/water logP o/w: 1,6
- · 12.4 Mobility in soil: No further relevant information available.
- · 12.5 Results of PBT and vPvB assessment:
- · **PBT:** PBT assessment not available.
- · **vPvB**: vPvB assessment not available.
- 12.6 Endocrine disrupting properties: For information on endocrine disrupting properties see section 11.
- · 12.7 Other adverse effects:
- Additional ecological information:
- · General notes:

Do not allow product to reach ground water, water course or sewage system.

Water hazard class 2 (German Regulation) (Assessment by list): hazardous for water.

SECTION 13: Disposal considerations

- · 13.1 Waste treatment methods
- · Recommendation

Disposal must be made according to official regulations.

Must not be disposed of together with household garbage. Do not allow product to reach sewage system.

- · Uncleaned packagings:
- · Recommendation:

Disposal of uncleaned packagings must be made according to official regulations in the same manner as the product.

• Recommended cleansing agent: Water, if necessary with cleansing agents.

14.1 UN number or ID number		
ADR, IMDG, IATA	Void	
14.2 UN proper shipping name		
ADR, IMDĞ, IATA	Void	
14.3 Transport hazard class(es)		
ADR, ADN, IMDG, IATA		
Class:	Void	
14.4 Packing group		
ADR, IMDG, IATA	Void	

Printing date 07.09.2022

Version number 4

Revision: 07.09.2022

Trade name: Dodecylsulfate-Na-salt

	(Contd. o	f page 6)
 14.5 Environmental hazards Marine pollutant: 	No	
· 14.6 Special precautions for user	Not applicable.	
• 14.7 Maritime transport in bulk according to IMO instruments Not applicable.		
· UN "Model Regulation":	Void	

SECTION 15: Regulatory information

- · 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture
- · Directive 2012/18/EU
- · Named dangerous substances ANNEX I Substance is not listed.
- DIRECTIVE 2011/65/EU on the restriction of the use of certain hazardous substances in electrical and electronic equipment Annex II Substance is not listed.
- · REGULATION (EU) 2019/1148
- Annex I RESTRICTED EXPLOSIVES PRECURSORS (Upper limit value for the purpose of licensing under Article 5(3)) Substance is not listed.
- Annex II REPORTABLE EXPLOSIVES PRECURSORS Substance is not listed.
- Regulation (EC) No 273/2004 on drug precursors Substance is not listed.
- Regulation (EC) No 111/2005 laying down rules for the monitoring of trade between the Community and third countries in drug precursors Substance is not listed.
- · National regulations:
- Water hazard class: Water hazard class 2 (Assessment by list): hazardous for water.
- · 15.2 Chemical safety assessment: A Chemical Safety Assessment has not been carried out.

SECTION 16: Other information

This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.

- · Department issuing SDS: Product safety department
- · Contact: +49 6221 13840-35
- Date of previous version: 02.05.2018
- Version number of previous version: 3
- Abbreviations and acronyms:

RID: Règlement international concernant le transport des marchandises dangereuses par chemin de fer (Regulations Concerning the International Transport of Dangerous Goods by Rail)

- vPvB: very persistent, very bioaccumulative substance (REACH)
- REACH: Regulation concerning the Registration, Evaluation, Authorisation and Restriction of Chemicals
- CLP: Regulation on classification, labelling and packaging of substances and mixtures
- bw: body weight

ADR: Accord relatif au transport international des marchandises dangereuses par route (European Agreement Concerning the International Carriage of Dangerous Goods by Road)

- IMDG: International Maritime Code for Dangerous Goods
- IATA: International Air Transport Association
- GHS: Globally Harmonised System of Classification and Labelling of Chemicals
- EINECS: European Inventory of Existing Commercial Chemical Substances CAS: Chemical Abstracts Service (division of the American Chemical Society)
- LC50: Lethal concentration, 50 percent
- LD50: Lethal dose, 50 percent
- PBT: Persistent, Bioaccumulative and Toxic
- vPvB: very Persistent and very Bioaccumulative

(Contd. on page 8)

ICAO: International Civil Aviation Organisation

PBT: persistent, bioaccumulative, toxic substance (REACH)

GB

Printing date 07.09.2022

Version number 4

Revision: 07.09.2022

Trade name: Dodecylsulfate-Na-salt

Acute Tox. 4: Acute toxicity – Category 4 Skin Irrit. 2: Skin corrosion/irritation – Category 2 Eye Dam. 1: Serious eye damage/eye irritation – Category 1 STOT SE 3: Specific target organ toxicity (single exposure) – Category 3 Aquatic Chronic 3: Hazardous to the aquatic environment - long-term aquatic hazard – Category 3 (Contd. of page 7)

GB -